

SILIPORITE® NK 30 BEADS

Product Data Sheet

PRODUCT BENEFITS

SILIPORITE® NK 30 is a synthetic zeolite type A of crystalline structure in Potassium-Sodium form, having an effective pore opening approximately of 3 angströms (3Å).

SPECIFICATIONS

	Unit	Values				Test control
BEADS / STANDARD GRAIN SIZE		1.6 mm	1.3 mm	1.0 mm	0.7 mm	
Particle size distribution retained	% weight					
- 0.5 mm		-	-	-	90 min	009
- 0.8 mm		-	-	75 min	-	
- 1.0 mm		-	85 min	-	2 max	
- 1.25 mm		-	-	5 max	-	
- 1.4 mm		85 min	-	-	-	
- 1.6 mm		-	10 max	-	-	
- 2.0 mm		10 max	-	-	-	
Delta-T (50 g MS / 50 cc water)	(°C)	37 min	37 min	37 min	37 min	004
Loss on ignition (1 hour at 540°C)	% weight	1.7 max	1.7 max	1.7 max	1.7 max	001
Available water adsorption capacity (AWAC)						
- at 10 % RH (2.375 mm Hg) 23°C +/- 2°C	% weight	16.0 min	16.0 min	16.0 min	16.0 min	002
Gas desorption at 70°C	cm ³ /100 gr	30 max	30 max	30 max	30 max	015

TYPICAL PHYSICAL PROPERTIES

	Unit	Values				Test control
DUST / FINE PARTICLES						
- 0.5 mm sieve opening	mg/100 gr	20	20	-	-	009
- 0.4 mm sieve opening	mg/100 gr	-	-	20	20	009
BULK DENSITY	g/cm ³	0.70 – 0.76	0.70 – 0.76	0.70 – 0.76	0.70 – 0.76	006

• SILIPORITE® NK 30 BEADS

APPLICATIONS

SILIPORITE® NK 30 BEADS can be used as desiccant in:

- Building:
 - Insulating Glass Units with inner spacer.
 - Door windows for refrigerators.
- Fine Chemicals / Pharmaceuticals:
 - Drying of solvents.

STANDARD PACKAGING

SILIPORITE® NK 30 BEADS is delivered in waterproof drums and boxes or in bag as follows:

Box	Net weight: 25 kg / 1 200 kg
Metallic drum	Net weight: 130 kg / 1 040 kg
Big bag	Net weight: 600 kg or 1 000 kg

FOR MORE INFORMATION

Contact your ARKEMA representative or ARKEMA's Molecular Sieves Department:

Telephone: +33 (0) 1 49 00 38 00

Fax: +33 (0) 1 49 00 38 03

E-mail: molecular.sieves@arkema.com

Version: 10 – March 2017

® Registered trademark of ARKEMA.

© 2015 ARKEMA. All rights reserved.

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement. See SDS for Health & Safety Considerations.

Arkema has implemented a Medical Policy regarding the use of Arkema products in Medical Devices applications that are in contact with the body or circulating bodily fluids (<http://www.arkema.com/en/social-responsibility/responsibleproduct-management/medical-device-policy/index.html>) Arkema has designated Medical grades to be used for such Medical Device applications. Products that have not been designated as Medical grades are not authorized by Arkema for use in Medical Device applications that are in contact with the body or circulating bodily fluids. In addition, Arkema strictly prohibits the use of any Arkema products in Medical Device applications that are implanted in the body or in contact with bodily fluids or tissues for greater than 30 days. The Arkema trademarks and the Arkema name shall not be used in conjunction with customers' medical devices, including without limitation, permanent or temporary implantable devices, and customers shall not represent to anyone else, that Arkema allows, endorses or permits the use of Arkema products in such medical devices.

It is the sole responsibility of the manufacturer of the medical device to determine the suitability (including biocompatibility) of all raw materials, products and components, including any medical grade Arkema products, in order to ensure that the final end-use product is safe for its end use; performs or functions as intended; and complies with all applicable legal and regulatory requirements (FDA or other national drug agencies) It is the sole responsibility of the manufacturer of the medical device to conduct all necessary tests and inspections and to evaluate the medical device under actual end-use requirements and to adequately advise and warn purchasers, users, and/or learned intermediaries (such as physicians) of pertinent risks and fulfill any postmarket surveillance obligations. Any decision regarding the appropriateness of a particular Arkema material in a particular medical device should be based on the judgment of the manufacturer, seller, the competent authority, and the treating physician.

ARKEMA

89, boulevard National

92257 La Garenne-Colombes Cedex - France

arkema.com

SILIPORITE®
BY ARKEMA